IKRAM PAVES SDN BHD

PAVEMENT LABORATORY

STANDARDS MALAYSIA

MS ISO/IEC 17025

TESTING

SAMM No. 762

LABORATORY TEST REPORT COVER PAGE

Report No.:	E2322
Total Pages :	*TWO (Excluding this page)*
Date Issued:	19/7/2022
Customer	DJX SOLUTIONS SDN BHD
Prepared For	-
Project Title	PLUS HIGHWAY

PRIVATE AND CONFIDENTIAL

This report and the methodologies it contain are the intellectual property of Pavement Laboratory, IKRAM PAVES Sdn Bhd and are intended solely to illustrate our approach to the proposed assignment. They may not be used or reproduced by any other party to undertake the assignment or for any other purpose without the express permission in writing from the General Manager, Pavement Laboratory of IKRAM PAVES Sdn Bhd or his nominee.

IKRAM PAVES SDN BHD
PAVEMENT LABORATORY

STANDARDS MALAYSIA
MS ISO/IEC 17025
TESTING
SAMM No. 762

LABORATORY TEST REPORT

Report No.	E2322	Date Issued:	19-Jul-22
Total No. of Pages	2	Page No.	1 of 2
Name And Address of Customer *(As Given By Customer)*	DJX SOLUTIONS SDN BHD UNIT 5 - 3 , DATARAN MUTIRA, JALAN 7/4 SERDANG JAYA, 43300 SRI KEMBANGAN SELANGOR DARUL EHSAN TEL : 019 9860958 EMAIL: -		
Title of Report *(As Given By Custormer)*	PLUS HIGHWAY		
Request No.	E2322		
Sample Received Date	6/7/2022		
Received by	RACMAWATI BINTI OTHMAN		
Test Commencement Date	6-Jul-22		
Test Completion Date	19-Jul-22		
Tested by	RACMAWATI BINTI OTHMAN		

Particulars Of Sample *(As Given by Customer)*						Pavement Laboratory
No.	Material (s)	Grade	Type	Qty.	Sample Marking	Sample ID
1	BITUMEN EMULSION	CG-BOND	LIQUID	3 Ltr	GC-1, GC-2, GC-3, GC-4, GC-5, GC-6, GC-7, GC-8, GC-9, GC-10 P-1, SP-1	E/S/1/C/1-1/23/22

Laboratory Testing(s)		
	Test(s) Carried Out	Test Method(s)
1	STANDARD TEST METHOD FOR WATER CONTENT*	1. -
2	STANDARD TEST METHOD FOR SETTLEMENT & STORAGE STABILITY OF EMULSIFIED ASPHALT - OVEN TEST METHOD	2. ASTM: D6930 - 19
3	STANDARD TEST METHOD FOR SAYBOLT FUROL VISCOSITY*	3. ASTM: D 244 CLAUSE 24-25
4	STANDARD TEST METHOD FOR SIEVE TEST (RESIDUE ON 850um)*	4. ASTM: D 244 CLAUSE 40-43
5	STANDARD TEST METHOD FOR PARTICLE CHARGE*	5. ASTM: D 244 CLAUSE 23-26.6
6	STANDARD TEST METHOD FOR PENETRATION OF BITUMINOUS MATERIALS	6.ASTM:D5 / D5M-20 (2020)
7	STANDARD TEST METHOD FOR SOFTENING POINT OF BITUMEN (RING AND BALL APPARATUS)	7. ASTM:D36/ D 36M - 14(2020)

Remarks: 1. * *NOT SAMM ACCREDITED SCOPE*
2. The test results apply to the sample as received from customer

IKRAM PAVES SDN BHD (Pavement Laboratory)
Approved Signatory

MOHD NASIR BIN REBU
Technical Manager

STATEMENTS OF CONFORMITY

"Statements of conformity (e.g. Pass/Fail/Indeterminate) to specifications are made in the laboratory test report by taking Measurement Uncertainty into account. Where statements of conformity are made in the laboratory test report, the following decision rules are applied

PASS : Results ± expanded uncertainty within limits/specifications
FAIL : Results ± expanded uncertainty exceeds limits/specifications
INDETERMINATE : Results ± expanded uncertainty overlaps limits/specifications"

This laboratory test report covers test samples, which were received and tested by Pavement Laboratory of IKRAM PAVES SDN. BHD. ONLY and this report IS NOT an approval certificate. This laboratory test report, except in full, shall not be reproduced without prior written approval from the General Manager (Pavement Laboratory) of Ikram Paves Sdn. Bhd.

Ikram Paves Sdn Bhd (Laboratory)
Block B, Unipark Suria,
Jalan Ikram-Uniten, 43000 Kajang, Selangor, Malaysia.
Tel: +603 8738 3371 • Fax: +603 8926 6282
email: ices.pav-lab@ikram.com.my
www.ikram.com.my

LABORATORY TEST REPORT

Test Report No.	**E2322**	**Request No.**	**E2322**	
Test Commencement Date:	**6-Jul-22**	**Test Completion Date**	**19-Jul-22**	**Pages : 2 of 2**
Title of Report:	**PLUS HIGHWAY**			

STANDARD TEST METHOD FOR WATER CONTENT*

STANDARD TEST METHOD FOR SETTLEMENT & STORAGE STABILITY OF EMULSIFIED ASPHALT - OVEN TEST METHOD

STANDARD TEST METHOD FOR SAYBOLT FUROL VISCOSITY*

STANDARD TEST METHOD FOR SIEVE TEST (RESIDUE ON 850um)*

STANDARD TEST METHOD FOR PARTICLE CHARGE*

STANDARD TEST METHOD FOR PENETRATION OF BITUMINOUS MATERIALS

STANDARD TEST METHOD FOR SOFTENING POINT OF BITUMEN (RING AND BALL APPARATUS)

Test No.	Material	Sample ID	Specimen Marking	Test	Test Method	Result	Spesification own by manufacturer	
							Min.	Max.
1	Bitumen Emulsion CG-BOND	E/S/1/C/1-1/23/22	GC-1, GC-2, GC-3	Water Content, %	-	Avg: 25.0 %	-	40%
2	Bitumen Emulsion CG-BOND	E/S/1/C/1-1/23/22	GC-4, GC-5	Storage Stability 24h, %	ASTM: D-6930-19	0.07 %	-	-
3	Bitumen Emulsion CG-BOND	E/S/1/C/1-1/23/22	GC-6	Saybolt Furol Viscosity (s), 25°C	ASTM:D 244	29.68 s	15	50
4	Bitumen Emulsion CG-BOND	E/S/1/C/1-1/23/22	GC-7	Sieve Test, % (Residue on 850um)	ASTM: D-244	0.026 %	-	0.1
5	Bitumen Emulsion CG-BOND	E/S/1/C/1-1/23/22	GC-8	Particle Charge	ASTM: D244	Positive	Positive	
6	Bitumen Emulsion CG-BOND	E/S/1/C/1-1/23/22	GC-9, GC-10	Settlement, 5 day, %	ASTM:D6930-19(2019)	0.08 %	-	-
7	Bitumen Emulsion CG-BOND	E/S/1/C/1-1/23/22	P-1	Penetration, 25°C, 100g, 5s,dmm	ASTM: D5/D 5M-19a	43.6 dmm	40	90
8	Bitumen Emulsion CG-BOND	E/S/1/C/1-1/23/22	SP-1	Softening Point,5°C	ASTM: D36	56.0 °C	54	-

Humidity/Temperature during testing (66 % / 28°C).

** The reported Measurement of Uncertainty is based on Standard Uncertainty of confidence level not less than 95% and subject to customer's request

** NOT SAMM ACCREDITED SCOPE*

Name : **Shahabudin Mohd Saini**	Nama : **Mohd Nasir bin Rebu**
Designation : **Laboratory Engineer**	Designation : **Laboratory Manager / Approved Signatory**
Date: : 19/7/22	Date : 19/07/2022